

# LOCTITE EDAG 1020A E&C

September 2012

## PRODUCT DESCRIPTION

LOCTITE EDAG 1020A E&C provides the following product characteristics:

<b>Technology</b>	Acrylate
<b>Appearance</b>	Transparent blue
<b>Product Benefits</b>	<ul style="list-style-type: none"> <li>• Screen printable</li> <li>• High breakdown voltage</li> <li>• Solvent resistant</li> <li>• UV curable</li> <li>• Excellent flexibility</li> <li>• Excellent printability</li> <li>• Excellent moisture resistance</li> <li>• Excellent adhesion to polyester film</li> </ul>
<b>Cure</b>	Ultraviolet (UV) light
<b>Application</b>	Dielectric coating
<b>Typical Assembly Applications</b>	Protective coating for membrane tails

LOCTITE EDAG 1020A E&C dielectric coating is formulated to provide electrical insulation on flexible circuitry. It is designed to print multi-layered circuits and conductive crossovers. LOCTITE EDAG 1020A E&C is compatible with other LOCTITE EDAG inks.

## TYPICAL PROPERTIES OF UNCURED MATERIAL

Solids Content, %	100
Viscosity, Brookfield, 25 °C, mPa·s (cP):	
Spindle 5, speed 20 rpm,	6,000
Density:	
lbs/gal	8.04
kg/l	1.05
Shelf Life (from date of qualification in original seal):	
@ 25°C, days	548

## TYPICAL SCREEN PRINTING PROCESS

### Recommended Screen Type

Polyester screen, mesh 160 to 280

### Emulsion Type

Solvent resistant emulsion

### Recommended Film Thickness

Total Film Thickness,  $\mu\text{m}$  25 to 38

A double pass (cured between passes) is suggested for electrical insulation applications. Each pass should have a thickness of 12.7 to 20.3 $\mu\text{m}$  per pass.

## TYPICAL CURING PERFORMANCE

### Recommended UV Cure

Light Dose, EIT radiometer, mJ/in<sup>2</sup> 400 to 500

The above cure profile is a guideline recommendation. Cure conditions (time and temperature) may vary based on customers' experience and their application requirements, as well as customer curing equipment, oven loading and actual oven temperatures.

## TYPICAL PROPERTIES OF CURED MATERIAL

### Physical Properties

Theoretical Coverage, sq ft/gal 1,600

### Electrical Properties

Dielectric Strength, volts/mil >1,000

Insulation Resistance, meg-ohms >1,000

## GENERAL INFORMATION

**For safe handling information on this product, consult the Material Safety Data Sheet, (MSDS).**

## DIRECTIONS FOR USE

1. Stir LOCTITE EDAG 1020A E&C prior to each use.
2. Bring product to room temperature prior to use.
3. Flammable. Keep away from heat, sparks and open flame.

## Clean-up

To clean screen and equipment, use Methyleneethylketone (MEK) and other suitable solvents

## Storage

Store product in the unopened container in a dry location. Storage information may be indicated on the product container labeling.

### Optimal Storage : 25 °C Keep from freezing.

Material removed from containers may be contaminated during use. Do not return product to the original container. Henkel Corporation cannot assume responsibility for product which has been contaminated or stored under conditions other than those previously indicated. If additional information is required, please contact your local Technical Service Center or Customer Service Representative.

## Not for product specifications

The technical data contained herein are intended as reference only. Please contact your local quality department for assistance and recommendations on specifications for this product.

**Conversions**

$(^{\circ}\text{C} \times 1.8) + 32 = ^{\circ}\text{F}$   
 $\text{kV/mm} \times 25.4 = \text{V/mil}$   
 $\text{mm} / 25.4 = \text{inches}$   
 $\text{N} \times 0.225 = \text{lb}$   
 $\text{N/mm} \times 5.71 = \text{lb/in}$   
 $\text{N/mm}^2 \times 145 = \text{psi}$   
 $\text{MPa} = \text{N/mm}^2$   
 $\text{MPa} \times 145 = \text{psi}$   
 $\text{N}\cdot\text{m} \times 8.851 = \text{lb}\cdot\text{in}$   
 $\text{N}\cdot\text{m} \times 0.738 = \text{lb}\cdot\text{ft}$   
 $\text{N}\cdot\text{mm} \times 0.142 = \text{oz}\cdot\text{in}$   
 $\text{mPa}\cdot\text{s} = \text{cP}$

**Disclaimer****Note:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. The product can have a variety of different applications as well as differing application and working conditions in your environment that are beyond our control. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Belgium NV, Henkel Electronic Materials NV, Henkel Nederland BV, Henkel Technologies France SAS and Henkel France SA please additionally note the following:**

In case Henkel would be nevertheless held liable, on whatever legal ground, Henkel's liability will in no event exceed the amount of the concerned delivery.

**In case products are delivered by Henkel Colombiana, S.A.S. the following disclaimer is applicable:**

The information provided in this Technical Data Sheet (TDS) including the recommendations for use and application of the product are based on our knowledge and experience of the product as at the date of this TDS. Henkel is, therefore, not liable for the suitability of our product for the production processes and conditions in respect of which you use them, as well as the intended applications and results. We strongly recommend that you carry out your own prior trials to confirm such suitability of our product.

Any liability in respect of the information in the Technical Data Sheet or any other written or oral recommendation(s) regarding the concerned product is excluded, except if otherwise explicitly agreed and except in relation to death or personal injury caused by our negligence and any liability under any applicable mandatory product liability law.

**In case products are delivered by Henkel Corporation, Resin Technology Group, Inc., or Henkel Canada Corporation, the following disclaimer is applicable:**

The data contained herein are furnished for information only and are believed to be reliable. We cannot assume responsibility for the results obtained by others over whose methods we have no control. It is the user's responsibility to determine suitability for the user's purpose of any production methods mentioned herein and to adopt such precautions as may be advisable for the protection of property and of persons against any hazards that may be involved in the handling and use thereof. In light of the foregoing, **Henkel Corporation specifically disclaims all warranties expressed or implied, including warranties of merchantability or fitness for a particular purpose, arising from sale or use of Henkel Corporation's products. Henkel Corporation specifically disclaims any liability for consequential or incidental damages of any kind, including lost profits.** The discussion herein of various processes or compositions is not to be interpreted as representation that they are free from domination of patents owned by others or as a license under any Henkel Corporation patents that may cover such processes or compositions. We recommend that each prospective user test his proposed application before repetitive use, using this data as a guide. This product may be covered by one or more United States or foreign patents or patent applications.

**Trademark usage**

Except as otherwise noted, all trademarks in this document are trademarks of Henkel Corporation in the U.S. and elsewhere. ® denotes a trademark registered in the U.S. Patent and Trademark Office.

Reference 0.1