

# Texiplast Fluo Plus PF

Code 16580-

## PRODUCT DESCRIPTION

Series of plastisol fluorescent inks for textile printing.

## APPLICATION FIELDS

Direct textile printing. For ready-to-wear or pre-cut articles.

## APPLICATION PROCESS

<b>Substrates</b>	<ul style="list-style-type: none"> <li>• Cotton 100%</li> <li>• Cotton mixed with synthetic fibers</li> <li>• Substrates have to be white</li> </ul>
<b>Th/cm</b>	<ul style="list-style-type: none"> <li>• Max. 43 Th/cm (110 Th/in)</li> </ul>
<b>Emulsion</b>	<ul style="list-style-type: none"> <li>• See reference table</li> </ul>
<b>Squeegee</b>	Square edge <ul style="list-style-type: none"> <li>• Squeegee hardness 60-65 shores</li> </ul>
<b>Curing</b>	<ul style="list-style-type: none"> <li>• 150/160°C for 3/2 minutes</li> </ul>
<b>Auxiliaries</b>	<ul style="list-style-type: none"> <li>• See TDS "<b>Texiplast Auxiliaries</b>"</li> </ul>
<b>Cleaning</b>	<ul style="list-style-type: none"> <li>• <b>Screenclean ST</b></li> </ul>
<b>Storage</b>	<ul style="list-style-type: none"> <li>• Away from direct sunlight</li> <li>• At a temperature between 15-35°C</li> </ul>
<b>Package</b>	<ul style="list-style-type: none"> <li>• See table "product range"</li> </ul>
<b>Safety Data Sheet</b>	<ul style="list-style-type: none"> <li>• Available upon Request</li> </ul>

## GENERAL FEATURES

- Bright fluorescent effect
- Good opacity
- Good elasticity
- Soft touch

## PREPARATION

Ready-to-use ink.  
Homogenize well, before using it.

## APPLICATION

For the best colour opacity and brightness, during printing, it is recommended to adjust the out of contact and the pressure of the squeegee at their best, in order to obtain an ink film that can remain onto the surface of the substrate.

The opacity is influenced by the kind of drawing, the th/cm screen number, the squeegee, the pressure and the printing speed.

Onto a dark substrate, it is recommended to overprint the inks of the series *Texiplast Fluo Plus Pf* into a white background. For such application, The use of *Texiplast 7000 White Flash Cure* or *Texiplast 7000 White Flash LT* (see the related technical data sheet) is recommended.

## CURING

Curing must take place at 150/160 for 3/2 minutes. *Texiplast* are thermoplastic inks: only an appropriate curing is able to allow the complete ink fusion, therefore the achievement of the required final characteristics.

## SPECIAL INSTRUCTIONS

- Always test the printing characteristics, before starting production.
- Always check curing conditions. The addition of additives could require higher temperature or longer time.
- Plastisol inks do not resist dry cleaning, bleaching and ironing.
- The inks of the series *Texiplast PF* are phthalate-free.
- Before using them, make sure that squeegees, counter squeegees, screens and cases have been cleaned well from possible rests of other plastisol series. In that way, possible “pollution”, deriving from other ink series, can be avoided.

## PRODUCT RANGE

Code	Texiplast Fluo PF	Package
165805	Yellow PF	5 kg
165806	Bright Orange PF	5 kg
165807	Red PF	5 kg
165808	Pink PF	5 kg
165809	Green PF	5 kg

## EQUIPMENT

Indicated for using onto automatic, semi-automatic and manual machines.

## IMPORTANT NOTE

The information given in this technical sheet is not intended to be exhaustive and any person, using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us to the suitability of the product for the intended purpose, does so at his own risk.

While we endeavour to ensure that all advice we give about the product is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage arising out of the use of the product.

The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

## WARNING

This technical data sheet does not replace either the Safety Data Sheet or the specific Conformity Declaration. These documents may be required to our SHEQ (Product safety office), at the following e-mail address: [safety@eptainks.com](mailto:safety@eptainks.com).

The technical data sheet does not relieve the printer, who remains the only responsible of the respect of the regulations, the specifications and the related required certifications of the finished items.