

# UV Stone NF

Code M415011NF

## PRODUCT DESCRIPTION

UV transparent matt varnish, with rough effect.

## APPLICATION FIELDS

UV Stone is indicated for packaging personalization or offset print ennobling, when a rough or “sandpaper” effect is required.

## APPLICATION PROCESS

<b>Substrates</b>	PAPER, PAPERBOARD, PVC, ABS, PET, PES, PS, PC, PMMA, PETG.
<b>Th/Cm</b>	From 43 to 77 Th/cm
<b>Emulsion</b>	See the product range table
<b>Squeegee</b>	Square edge Squeegee hardness 70-75 Shores
<b>Curing</b>	UV lamps from 80 to 120 W/cm Carpet speed: 15-20 m/min Power: at least 250 Mj/cm <sup>2</sup>
<b>Thinners</b>	Reactive Thinner 100.900 (code A31810090000...) Max. 5%
<b>Auxiliaries</b>	Concentrated Photoinitiator UV 100.978
<b>Adhesion promoters</b>	Adhesion Promoter 100.835 (code A318100835001) Max. 5%
<b>Cleaning</b>	Solvent LQ 90.920
<b>Storage</b>	If kept in a dark place, in its original sealed package, at a temperature of 20-25°C, the product has a shelf-life of about 1 year.
<b>Packaging</b>	5 kg
<b>Safety data sheet</b>	Available upon request

## PREPARATION

Before using it, the ink must be mixed well and, in case, diluted, according to printing requirements. In case that viscosity reduction is needed, it is possible to add up to 5% Reactive Thinner 100.900.

## GENERAL FEATURES

- Matt finishing
- Excellent scratching resistance
- Good flexibility
- Excellent rough effect

## TECHNICAL FEATURES

The performance of the product, printed with a 77 th/cm screen, is 35-40 m<sup>2</sup>/kg. These data are merely an indication, since they depend on the dilution, the substrate and the printing equipment. In case that an increase in the ink reactivity is needed, it is possible to add up to 5% Concentrated Photoinitiator 100978.

## SPECIAL RECOMMENDATIONS

- Always test the characteristics of the product, before starting production.
- The above information is the result of previous knowledge and experience; it is neither a guarantee nor an assurance.
- In order to improve adhesion on such substrates, that are difficult to be printed, it is recommended to add 5% of Adhesion Promoter 100.835 (pot-life 4-8 hours).

## IMPORTANT NOTE

The information given in this technical sheet is not intended to be exhaustive and any person, using the product for any purpose other than that specifically recommended in this sheet without first obtaining written confirmation from us of the suitability of the product for the intended purpose, does so at his own risk.

While we endeavour to ensure that all advice we give about the product is correct, we have no control over either the quality or condition of the substrate or the many factors affecting the use and application of the product.

Therefore, unless we specifically agree in writing to do so, we do not accept any liability whatsoever or howsoever arising for the performance of the product or for any loss or damage arising out of the use of the product.

The information contained in this sheet is liable to modification from time to time in the light of experience and our policy of continuous product development.

## WARNING

This technical data sheet does not replace either the Safety Data Sheet or the specific Conformity Declaration. These documents may be required to our SHEQ (Product safety office), at the following e-mail address: [safety@eptainks.com](mailto:safety@eptainks.com)

The technical data sheet does not relieve the printer, who remains the only responsible of the respect of the regulations, the specifications and the related required certifications of the finished items.